



## C5 ALIPHATIC RESINS

Product	Type	Softening Point R&B, °C	Gardner Color*	Specific Gravity @ 25°C	Brookfield Viscosity, cPs	Molecular Weight Mn	Molecular Weight Mw
<b>NEVTAC® LT</b>	Liquid C5	8	4.5	0.902	24,000 @ 30°C	850	1,400
<b>NEVTAC® 10</b>	Liquid C5	12	5.5	0.95	76,000 @ 25°C	440	1,260
<b>NEVTAC® 100</b>	C5	100	3.5	0.97	430 @ 175°C	1,150	2,800
<b>Super NEVTAC® 99</b>	C5/C9	95	4.5	0.97	3,200 @ 150°C	1,000	2,300
<b>Super NEVTAC® 90</b>	C5/C9	90	4.0	0.97	3,060 @ 150°C	1,080	2,200

\*50% solution in Aromatic 100