



DCPD RESINS

Product	Type	Softening Point R&B, °C	Gardner Color*	Molecular Weight	
				Mn	Mw
LX®-2250	Liquid Maleated DCPD	N/A	8 (Straight)	N/A	N/A
LX®-3843	Liquid DCPD	N/A	11 (Straight)	N/A	N/A
LX®-3120	Liquid DCPD	20	12 (Straight)	N/A	N/A
LX-685®-125	DCPD	105	8	520	1,590
LX®-1055	DCPD	105	13	560	1,240
LX®-2600-105	DCPD	105	14	485	1,650
LX®-3100	DCPD	108	14	450	935
LX®-1144LV	DCPD	110	6	500	1,100
LX®-238	DCPD	113	8	520	1,590
LX®-1200	DCPD	114	11	465	1,480
LX-685®-135	DCPD	115	10	600	1,500
LX-1000®-130	DCPD	130	12	410	900
LX-1000®-140	DCPD	138	13	440	970
LX®-2120	DCPD	120	14	565	1,138
LX®-2140	DCPD	140	13	440	1,280
LX®-2181	DCPD	140	13	620	1,900
LX®-2600	DCPD	140	14	485	1,650
LX®-1035	DCPD	170	13	680	1,950

*50% solution in Aromatic 100