

Solubility of Neville Resins

S=Soluble I=Insoluble P=Partially Soluble

| | DCPD Thermal | C-9 Aromatic | C-5 Aliphatic | VERSADIL® Diluent | NEVOXY® Modifier |
|--------------------------|-----------------|-----------------|------------------|----------------------|---------------------|
| Ethers | S | S | S | P | S |
| Esters | S | S | S | P | S |
| Alcohols | I | I | I | I | S |
| Rule 66 Mineral Spirits | S | S | S | S | I |
| Xylene | S | S | S | S | S |
| Toluene | S | S | S | S | S |
| MIAK and MPK | S | S | S | S | S |
| TBA (tert butyl acetate) | S | S | P | P | I |
| Propylene Carbonate | I | S | S | S | I |
| Acetone | I | S | I | P | I |
| Soya Methyl Ester | S | S | S | P | S |
| Aromatic 100 Solvent | S | S | S | S | S |
| Napthahenic | S | S | S | S | S |
| Paraffinic | P | P | P | P | I |
| Oxxsol 100 | S | S | S | S | I |
| Diemthyl Carbonate | S | S | S | S | I |

Compatibility of Neville Resins

C=Compatible I=Incompatible P=Partially Compatible

| | DCPD Thermal | C-9 Aromatic | C-5 Aliphatic | VERSADIL® Diluent | NEVOXY® Modifier |
|-------------------------------|-----------------|-----------------|------------------|----------------------|---------------------|
| Long Oil Alkyd | C | C | P | C | P |
| Medium Oil Alkyd | C | C | P | C | P |
| Short Oil Alkyd | I | P | I | P | I |
| Acrylates | P | C | I | I | P |
| Cellulose Derivaties | I | I | I | I | I |
| Hydrocarbon polymers | C | C | C | C | C |
| Chlorinated Hydrocarbons | C | C | C | I | P |
| Elastomer, Syntheic & Natural | C | C | C | C | C |
| Waxes | C | C | C | C | C |
| Tar & Pitches | C | C | C | C | P |
| Epoxies | P | C | I | I | C |
| Rosin Resin & Derivaties | C | C | P | P | P |
| Phenolic Resins / Oil Soluble | C | C | C | C | C |
| Vinyl | P | P | P | P | P |
| Ester Plasticizers | C | C | C | P | C |