



CUMAR® AROMATIC RESINS Typical Properties

Product	Type	Softening Pt. R&B, °C	Gardner Color*	Specific Gravity @ 25°C	Brookfield Viscosity, cPs	Molecular Weight	
						Mn	Mw
CUMAR® P-10	Liquid Aromatic	13	11	1.04	1,300 @ 120°F	220	N/A
CUMAR® P-25	Liquid Aromatic	24	11	1.06	6,500 @ 120°F	260	N/A
CUMAR® 105	Aromatic	104	11	1.08	1,065 @ 160°C	520	1,325
CUMAR® 130	Aromatic	130	10	1.08	22,800 @ 160°C	780	1,800

*50% solution in Aromatic 100